



AN ISO 9001-2008 COMPANY
NON SHRINK GROUT ADMIXTURE NSG A-11

Cement mortar tends to shrink on setting. For many applications this shrinkage is not acceptable.

Non Shrink Grout Admixture NSG A-11 is specially designed to provide controlled expansion when added to cement mortar.

Mix cement, sand, metal, as usual, Add 250gm NSG A-11 to this Mortar, Mix thoroughly, add water as desired, cast as usual.

Non Shrink Grout Admixture NSG A-11 has no deleterious influence on concrete strength, the controlled expansion merely off sets the shrinkage associated with hydration.

Non Shrink Grout Admixture NSG A-11 may be used with Portland cement or pozolona cement.

Non Shrink Grout Admixture NSG A-11 is available in 25 kgs polylined bags. It is recommended that the material should be stored in cool dry place, away from sharp object to avoid tearing of bags or damage to bags, unopened bags may be used upto 1 – 2 years from date of manufacture.

NO	PRODUCT – DATA	
1.	Colour	Greyish
2.	Specific gravity	3.00
3.	Mesh size	300 mesh
4.	Dosage	250gm per 50 kgs Cement
5.	Cement Compatibility	P.C.C, O.P.C
6.	Chloride, Sulphates	Nil

OTHER PRODUCTS

Tile Fix # 1 • Tile Fix # 1A • Tile Fix SP # 1 • Strextra NSG 110 •
Strextra - NSG 2024 • Easy Grout • Water Repellent WBWR – 2023 •
Water Repellent SBWR – 5000 • Shutter Coat for Wood & Metal •
Concrete Cure Coating – 111 • Concrete Cure Coating – 103 •
P.A. Bound • P.A. Mortar TH – 4 • PA. Mortar EF – 1 • P.A. Mortar
Slurry • Marble Fix • Floor Repair Mortar • Insta Plugging Mortar •
Pipe Joint Sealer • Tile Joint Sealer [Colour] – Red, White, Black,
Brown, Ivory, Green, Grey, Pink. • Metal Protect • RZ – Polymer
ED Mortar • Special Grouting System • Anti Hack Paint (XRG) •
Tuffar • ADMGP – 1 • P A – Resin 651XXX • Hak Safe AL 111 •
Paint Remover PR – 128 • COLGROUT Admixture CG – 101S •
Rock Splitting Grout ATC-A201 • Ready Plaster • Best Plaster Putty



It is strongly recommended that site trials be conducted using site conditions and available raw materials to evaluate the product. Since site materials and conditions are beyond our control and since above suggestions and recommendations are based on our site trials and laboratory product evaluation & trials, and since methods of use at site are beyond our control. Hence, no guarantee can either be implied or enforceable