

ALL SEAL (Multi Purpose Sealant)

ALL SEAL is a versatile single component, non sag, rapid grip, fast setting, high bond, elastic, flexible, water resistant, weather & ageing reisitant, paste based on PVA hybrid for sealing gaps, joints and cracks upto 2" without fracturing and easily absorbing distortions for all tropical climates. With its adhesion characteristics it borders the properties of an adhesive. It requires no external curing and is impermeable to water.

Applications:-

SEALING- FIXING – BONDING – JOINING

most household,/ construction,/ industrial materials such as aluminum, metal, glass, concrete, plasters, wood, tiles, ceramics, roofing sheets, PVC pipe joints, etc and

- Cracks in concrete, plaster, upto 10 mm or more.
- Sealing gaps between aluminum sheets or profiles used in variety of application like window frames and substrate, office cubicle sections; sealing glass in aluminum sections etc
- Bonding, fixing, joining and sealing non structural elements for aesthetics and water proof joints.
- Used for sealing gap between sink/ bathtub and vertical/horizontal tiles, replacing tiles on vertical surface, sealing gaps of door frames in the floors sealing joints of vertical

- tiles, drilled holes in tiles/ walls, pasting decorative wall papers and flooring mats etc..
- Seal Vertical and Horizontal joints/ cracks / pavement grooves upto 2" width
- Sealing all types of holes or joints/cracks, between asbestos/cement fibre corrugated sheets and U/J bolt holes.
- Sealing rivet joints & lap joints of various metals such as MS, aluminum, PVC sheets, checkered plates etc for watertight permanent joints in railway coaches, bus bodies etc.
- Sealing threads of PVC/ GI pipes to prevent leakages
- Ideal for HOUSEHOLD, CRAFT & HOBBIES, CONSTRUCTION, **INDUSTRIAL** applications

Advantages:-

- **Highly Elastic**
- Single Component, easy to use
- Non Sagging
- Fast Set
- Long Life

- ✓ Maintains its properties even upto 80^oCTemperatures
- ✓ Built for tropical climates
- ✓ High Flexibility
- ✓ Highest bond to most materials.

Surface Pre-Treatment & Method Of Application

On a clean, dry surface viz free of oils, grease and dust apply ALL-SEAL from its easy to use squeezee pouch/ tube. It is fast setting and adheres to most materials.

Once cured, the sealant's matrix becomes like a semi-flexible rubber, which is elastic and firm. It maintains a complete dense elastic &waterproof seal in tropical conditions for temperatures upto 50° C. It has very high bond strength to wide range of substrates. Once set, it could be painted upon easily.

Packing: Easy to use 0.2kg, 0.5 kg, and bulk packs of 1 kg, 4 kg, 20 kg, 200 kg drum packing

Coverage

Typical Coverage of ALL SEAL				
Width of groove/ crack	Depth of groove/crack			
W 17-12- 0- 8-00 / 0/ 0-11-12-	5mm	10mm	25 mm	
5mm	44 M	22 M	9 M	
10mm	18 M	9 M	3.5 M	
25 mm	7 M	3.5 M	1.5 M	

Technical Data

No	Characteristic	Property	
1.	Appearance	White, Grey & Black	
2.	Consistency	Non-Sag paste	
3.	Density	1.65 approx	
4.	Curing Times @ 30° C	Touch Dry within 0.5 hours	
	(depends upon substrate)	Hard Dry 24 hours	
		Full cure 7 days	
5.	Shrinkage	Not more than 2%	
6.	Glass Transition temperature	-8 °C	
7.	Service Temperatures	1 ° C to 80 ° C	
8.	Shore A Hardness	About 55	
9.	Elasticity	> 150% before fracture	
10.	Resistance to UV rays and water	Excellent	
11.	Adhesion to materials such as concrete,	Excellent	
	glass, metals, aluminium, wood, ceramic,	20	
	asbestos, POP, card-paper, fiber sheets,	-	
12.	Bond strength between aluminum sheets	0.13 MPa after 24 hours @ 32 ° C	
		0.5 MPa after 7 days	
13.	Tensile Strenght	2 MPa approx	
14.	Shelf Life	12 months if stored in cold dry place away	
		from sunlight in tightly sealed containers.	

OTHER PRODUCTS:-

- Waterproofing systems
- High Strength cementatious repair mortars
- Range of Industrial & Civil Maintenance systems
- Tremix (Floor) surface hardners

- Corrosion protective coatings
- Admixtures for concrete
- **Paints** Epoxy Paints...
- * Range of 1200 different products



RAZON ENGINEERING COMPANY PRIVATE LIMITED

AN ISO 9001-2008 COMPANY

